



Proquitec
Indústria, distribuição e representação.



Developing the
future with us

PRODUCTS Line

Poroso 

proquitec.com.br



BLOWING AGENTS

AZODICARBONAMIDE



BENEFITS / ADVANTAGES

- DOES NOT TRANSFER ODOR TO THE FINAL PRODUCT
- DOES NOT STAIN
- NO DECORATION OF THE FINAL PRODUCT
- GENERATES UNIFORM CELLS
- HIGH GENERATION OF GAS

APPLICATIONS

- EXPANDED RUBBER "MICROCELLULAR"
- EXPANDED EVA
- EXPANDED LDPE
- PVC LAMINATED
- EXPANDED PVC
- EPDM PROFILES
- EXPANDED IN GENERAL



PROPERTY

Poroso AZBR

| | | |
|-----------------|-------------|--------|
| Appearance | - Powder | |
| Color | - Yellow | |
| Granulometry | - 6 - 9 | Micron |
| Gas Volume CNTP | - 220 - 245 | ml/g |
| Decomposition | - 200 | °C |

Poroso AZBR-3

| | | |
|-----------------|-------------|--------|
| Appearance | - Powder | |
| Color | - Yellow | |
| Granulometry | - 3 - 4 | Micron |
| Gas Volume CNTP | - 220 - 245 | ml/g |
| Decomposition | - 200 | °C |

Poroso SC-C

| | | |
|-----------------|-------------|--------|
| Appearance | - Powder | |
| Color | - Yellow | |
| Granulometry | - 25 - 30 | Micron |
| Gas Volume CNTP | - 180 - 200 | ml/g |
| Decomposition | - 160 | °C |

Poroso P-80

| | | |
|-----------------|-------------|--------|
| Appearance | - Powder | |
| Color | - Yellow | |
| Granulometry | - 6 - 9 | Micron |
| Gas Volume CNTP | - 180 - 200 | ml/g |
| Decomposition | - 150 | °C |